



Meade-King, Robinson & Co. Ltd.

Tower Building, 22 Water Street, Liverpool, L3 1BL
Tel: 0151 236 3191, Fax: 0151 236 4431 / 0151 227 1438
Email: chris@mkr.co.uk, Web: www.mkr.co.uk

PRODUCT SPECIFICATION

Description: Carisma Jelly SilkySoft White Petroleum Jelly	Issue: 1 W 365
--	------------------------------

<u>Test Method</u>	<u>Specification</u>	<u>Typical</u>
Congealing Point, ASTM D938	48.0 – 56.0°C	50 - 51°C
Drop Melting Point, ASTM D127	47.0 – 62.0	50 – 51°C
Cone Penetration @ 25°C / dmm (IP179)	125 – 145	129
Kinematic Viscosity @ 100°C, ASTM D445	4.5 – 6.5 cSt	5 cSt
Colour Lovibond, IP17 yellow 1" cell	0.0 – 0.5	0.1
Colour Saybolt ASTM D6045	-	27
Visual Appearance	White paste	
Purity	Cosmetic Conforms to current European Pharmacopoeia	

NB: This document nullifies and replaces all previous documents referring to this product.