



Meade-King, Robinson & Co. Ltd.

Tower Building, 22 Water Street, Liverpool, L3 1BL
Tel: 0151 236 3191, Fax: 0151 236 4431 / 0151 227 1438
Email: chris@mkr.co.uk, Web: www.mkr.co.uk

PRODUCT SPECIFICATION

S.015

Description: **ETRO 4**
 Group III Base Oil

Issue: **1**

<u>Property</u>	<u>Method</u>	<u>Limits</u>
Appearance	Visual	Bright and Clear
ASTM Colour	ASTM D1500	0.5 max
Kinematic viscosity at 100°C, cSt	ASTM D445	4.15 – 4.35
Viscosity index	ASTM D2270	127 min
Pour point, °C	ASTM D97	-15 max
Flash Point, °C	ASTM D92	200 min
NOACK Volatility, wt %	ASTM D5800 Proc B	15 max
Saturates, wt %	HPLC	95 min
Sulphur, ppm	ASTM D2622	30 max

API Group III base oil

Formulation support for the latest low SAPS (sulphated ash, phosphorus, and sulphur). API, ACEA and OEM formulations.

NB: This document nullifies and replaces all previous documents referring to this product.