


LMO Slackwax (Stanlow)



Crude paraffins derived from petroleum solvate dewaxing are used in applications where color and residual oil content will be of minor importance, e.g. impregnation, coating or hydrophobing of industrial products.

Product data

Properties	Standard	Unit	Specification
Congealing point	ASTM D 938	°C	55 - 59
Oil content	ASTM D 721	%	max. 25
Viscosity at 100 °C	ASTM D 445/IP 71	mm ² /s	5.4 – 6.8
Color	ASTM D 1500	-	max. 4.0
Color	visual	-	yellow
Flash point, PM	ASTM D 93	°C	min. 220

We reserve the right to change the specification as a result of technical progress or for reasons related to production!
No guarantee or warranty is implied as to any particular applications of our products.