



# Meade-King, Robinson & Co. Ltd.

Tower Building, 22 Water Street, Liverpool, L3 1BL  
Tel: 0151 236 3191, Fax: 0151 236 4431 / 0151 227 1438  
Email: chris@mkr.co.uk, Web: www.mkr.co.uk

## PRODUCT SPECIFICATION

<b>Description:</b>	<b>Refined Montan Wax Waradur ELE</b>	<b>Issue:</b>	<b>2</b>
			<b>W.265</b>

### Characteristics

Acid value (mg KOH/g)	25 - 35
Saponification value (mg KOH/g)	110 - 140
Dropping point (°C)	82 - 88
Solidification point (°C)	72 – 80 (Typical)
Viscosity (mPas; 120°C)	10 – 20 (Typical)
Density (g/cm <sup>3</sup> )	1.00 – 1.02 (Typical)
Penetration value (dmm)	5 (Typical)
Colour	Pale Yellow